

Rust Veto® 344

Outdoor storage protection of steel surfaces

DESCRIPTION

This fast drying, solvent solution produces a hard .003" black, tough, plastic type film. It was developed to give long-term protection on equipment that is to be stored outdoors. Its rapid drying permits handling within four hours without injury to the film.

When exposed to long periods of outdoor storage the film is extremely resistant to cracking, "alligatoring" and/or flaking. A **Rust Veto 344** film will not flow up to 190°F, and remains plastic down to 0°F. Material coated with this product can be welded without removing the coating.

FEATURES / BENEFITS

- Excellent weathering
- Fast drying
- You can weld through film
- Good resistance to cracking
- Protects your investment in inventoried parts for years.
- Low-odor nature of the products optimizes worker acceptance.
- Rapid drying permits handling of parts shortly after application which expedites process flow and packaging.

DATA (TYPICAL VALUES)

Type of Film	Dry, black
Flash Point	105°F minimum (40.5°C min.)
Film Thickness (dip)	3.0 – 4.5 mils
Pour Point	20°F (-6.6°C)
Drying time	4 hours
Low temperature adhesion	Will not flake off at 0°F (-17.7°C)
Gravity @ 60°F	0.88
Coverage (average)	300 sq. ft./gal.
Pound per gallon	7.39 (.888 kg/l)

HEALTH AND SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local Houghton representative.

NOTE: Read and understand all precautions on container labels before using this product.

HL 13.08 US



Houghton International Inc.
 Madison and Van Buren Aves.
 P. O. Box 930
 Valley Forge, PA 19482-0930

Phone: 610-666-4000
 Fax: 610-666-0174
 info@houghtonintl.com
 www.houghtonintl.com

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.