

Rust Veto® 377-HF

Rust preventative

DESCRIPTION

Rust Veto 377-HF actually raises water off wet metal to coat the entire surface with a long-lasting film.

One gallon covers 1,300 square feet. The polar attraction for metal makes **Rust Veto 377-HF** "creep" across the metal's surface, spreading over a large area. The affinity for metal means handling won't wipe it off.

Rust Veto 377-HF contains an antioxidant additive. It resists breakdown and varnish formation, even in long-term storage.

Rust Veto 377-HF needs to be agitated prior to use to insure that the rust preventative film forming components are dispersed in the solvent carrier and uniformly applied to parts to be protected.

FEATURES / BENEFITS

- Low-odor nature of the products optimizes worker acceptance.
- Displaces water or process fluids from wet parts to rapidly begin the corrosion inhibition process.
- The high flash point reduces the potential for flammability and may reduce fire insurance premiums.

DATA (TYPICAL VALUES)

Film Thickness	0.0003" (0.0076 mm)
Film Character	Soft-greasy
Flash Point, PMCC	175°F
Viscosity @ 100°F	40 SUS
Pounds per Gallon	6.92
Specific Gravity 60°/60°F	.833
Coverage	1,300 sq. ft./gal. 29.5 sq. meter/liter
Pour Point	-42°F
Freeze Point	-47°F
ASTM D-1748 - Humidity @ 120°F	Passes 90+ days (typical)
ASTM B-117 - 5% Salt Spray	Passes 10 days (typical)

HL 13.12 US

HEALTH AND SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local Houghton representative.

NOTE: Read and understand all precautions on container labels before using this product.



Houghton International Inc.
 Madison and Van Buren Aves.
 P. O. Box 930
 Valley Forge, PA 19482-0930

Phone: 610-666-4000
 Fax: 610-666-0174
 info@houghtonintl.com
 www.houghtonintl.com

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.